


## IN THE CLAIMS

The following claim set replaces all prior versions, and listings, of claims in the application:


1. (Presently Amended) A branched polyacetal resin composition, comprising:  
100 parts by weight of a branched polyacetal copolymer (A) having an oxymethylene group as the main repeating unit and having a branching unit represented by the following formula (I), wherein the branched copolymer (A) is the copolymerization reaction product of 100 parts by weight of trioxane (a-1), 0.001 to 10 parts by weight of a monfunctional glycidyl compound (a-2) selected from the group consisting of a glycidyl ether compound represented by the following formulae (II), (III) and (IV), and a glycidyl ester compound, each having a molecular weight of 100 to 1000, and 0.1 to 20 parts by weight of a cyclic ether compound (a-3) which is copolymerizable with trioxane selected from the group consisting of ethylene oxide, 1,3-dioxolan, diethylene glycol formal and 1,4-butanediol formal, and  
0.5 to 40 parts by weight of at least one polymer (B) selected from the group consisting of the following polymers (B-1) and (B-2),  
polymer (B-1): a graft or block copolymer prepared from an olefin polymer ~~9b-1~~ (b-1) and at least one vinyl polymer (b-2); and  
polymer (B-2): a modified olefin polymer in which an olefin polymer (b-3) is modified with at least one compound selected from the group consisting of an unsaturated carboxylic acid, an unsaturated carboxylic acid anhydride and derivatives thereof, and/or

0.1 to 5 parts by weight of a lubricant (C), and wherein

formulae (I)-(IV) are as follows:




wherein m and n each is an integer of 0 to 5; the sum of m + n is 1 to 5;  
 and R is a monovalent organic group having a number-average  
 molecular weight of 40 to 1000,





---

wherein R<sup>1</sup> is a C<sub>1-12</sub> alkyl group, a substituted alkyl group, an alkoxy  
group, an aryl group, a substituted aryl group or halogen; and n is  
an integer of 0 to 5 and, when n is 2 or more, the R<sup>1</sup>'s may be the  
same or different:




---

wherein R<sup>2</sup> is a C<sub>1-30</sub> alkylene group, a substituted alkylene group or a  
polyalkylene oxide glycol residue; R<sup>3</sup> is a C<sub>1-12</sub> alkyl group, a  
substituted alkyl group, an alkoxy group, an aryl group, a  
substituted aryl group or halogen; and n is an integer of 0 to 5 and,  
when n is 2 or more, the R<sup>3</sup>'s may be the same or different:



---

wherein R<sup>4</sup> is a C<sub>1-30</sub> alkylene group; n is an integer of 0 to 20; and R<sup>5</sup> is a C<sub>1-30</sub> alkyl group, a C<sub>2-20</sub> alkenyl group or an alkynyl group.

2. (Canceled)
3. (Canceled)
4. (Canceled)
5. (Canceled)
6. (Canceled)
7. (Previously Amended) The composition according to claim 1, wherein the polymer (B-1) is prepared from at least one olefin polymer (b-1) selected from the group consisting of polyethylene, polypropylene and an ethylene-propylene copolymer, and at least one vinyl polymer (b-2) selected from the group consisting of methyl polymethacrylate, an acrylonitrile-styrene copolymer and polystyrene.
8. (Previously Amended) The composition according to claim 1, wherein the polymer (B-2) is a modified olefin polymer where 100 parts by weight of the olefin polymer (b-3) is modified with 0.1 to 20 parts by weight of maleic anhydride.
9. (Previously Amended) The composition according to claim 1, wherein the polymer (B-2) is a modified olefin polymer where at least one olefin polymer (b-3) selected from the group consisting of polyethylene, polypropylene, an ethylene-propylene copolymer, an ethylene-ethyl acrylate copolymer and an ethylene-methyl acrylate copolymer, is modified.